



## AEP Span Color Performance Data

The Cool Roof Rating Council (CRRC) website lists AEP Span SRI Initial and Three-year Aged information. Note - CRRC data is based on averaged color families and does not reflect the actual performance of each specific AEP Span color. Therefore, under the LEED column header actual Initial SRI values are provided and reflect actual performance of each color. If required, please note that color specific CRRC Notification of Product Rating letters can be produced upon request.

PRODUCT DESCRIPTION	CRRC and CA Title 24					CA Title 24	LEED							OTHER	
	via CRRC product approvals ( www.coolroofs.org )						via Accredited Independent Testing Laboratory (using ASTM C1549, C1371, & E1980)								
	CRRC Reference Number	Solar Reflect - ance (Init.)	Thermal Emitt - ance (Init.)	SRI Initial	SRI 3YR Aged		Solar Reflect - ance (Init.)	Thermal Emitt - ance (Init.)	SRI (Init.)	Low Slope	Steep Slope	3YR Aged SRI	Low Slope		Steep Slope
<b>BARE ZINCALUME®</b>															
ZINCALUME® Plus	1014-0002	0.68	0.30	64	46	REFER TO CALIFORNIA ENERGY COMMISSION (CEC) REQUIREMENTS	0.68	0.30	64		✓	46		✓	67
<b>DURA TECH™ NT COLORS</b>															
CHESTNUT BROWN	0818-0034	0.32	0.83	31	31		0.35	0.83	36			31			12
DENALI GREEN	0818-0028	0.25	0.83	22	22		0.30	0.83	29			22			11
DESERT BEIGE	0818-0042	0.45	0.83	49	48		0.51	0.84	58		✓	48		✓	39
LIGHT STONE	0818-0033	0.55	0.83	63	60		0.60	0.84	70		✓	60		✓	53
OLD TOWN GRAY	0818-0039	0.35	0.83	35	35		0.40	0.84	43		✓	35		✓	27
RUSTIC RED	0818-0031	0.35	0.83	35	35		0.40	0.84	43		✓	35		✓	13
SURF WHITE	0818-0036	0.55	0.83	63	60		0.63	0.84	74		✓	60		✓	59
TAHOE BLUE	0818-0027	0.25	0.83	22	22		0.33	0.84	33			22			14
WEATHERED COPPER	0818-0035	0.32	0.83	31	31		0.32	0.83	32			31			11
WINTER WHITE	0818-0044	0.70	0.83	84	75		0.73	0.83	88	✓	✓	75	✓	✓	74
<b>DURA TECH™ 5000 &amp; DURA TECH™ MX COLORS</b>															
COLONIAL RED	0818-0016	0.25	0.83	22	22		0.34	0.85	35			22			9
DARK BRONZE	0818-0018	0.25	0.83	22	22		0.32	0.84	32			22			8
FOREST GREEN	0818-0012	0.25	0.83	22	22		0.30	0.84	29			22			9
LEAF GREEN	0818-0015	0.25	0.83	22	22		0.30	0.85	30			22			11
MATTE BLACK	0818-0046	0.25	0.83	22	22		0.30	0.84	29			22			5
METALLIC CHAMPAGNE	0818-0038	0.35	0.75	32	32		0.48	0.84	54		✓	32		✓	33
METALLIC COPPER	0818-0006	0.35	0.75	32	32		0.48	0.83	53		✓	32		✓	29
METALLIC SILVER	0818-0003	0.35	0.75	32	32		0.57	0.82	65		✓	32		✓	50
MIDNIGHT BRONZE	0818-0055	0.25	0.83	22	22		0.28	0.84	27			22			7
OLD TOWN GRAY	0818-0009	0.35	0.83	35	35		0.40	0.85	43		✓	35		✓	27
PARCHMENT	0818-0047	0.45	0.83	49	49		0.51	0.84	58		✓	49		✓	40
PEBBLE	0818-0059	0.32	0.83	31	31		0.43	0.85	48		✓	31			27
REGAL BLUE	0818-0008	0.25	0.83	22	22		0.30	0.84	29			22			10
REGAL WHITE	0818-0049	0.70	0.83	84	79		0.73	0.84	88	✓	✓	79	✓	✓	75
SAGE GREEN	0818-0056	0.35	0.83	35	35		0.38	0.84	41		✓	35		✓	21
SIERRA TAN	0818-0020	0.45	0.83	49	49	0.49	0.84	55		✓	49		✓	34	
SILVERSMITH	0818-0058	0.35	0.75	32	32	0.52	0.82	58		✓	32		✓	54	
SLATE GRAY	0818-0057	0.25	0.83	22	22	0.32	0.85	33			22			12	
TAHOE BLUE	0818-0007	0.25	0.83	22	22	0.33	0.84	33			22			14	
TERRA COTTA	0818-0037	0.35	0.83	35	35	0.39	0.84	41		✓	35		✓	15	
VINTAGE®	1014-0003	0.30	0.70	22	21	0.30	0.70	22			21			20	
WALNUT	0818-0054	0.32	0.83	31	31	0.37	0.84	38			31			18	
WEATHERED COPPER	0818-0019	0.32	0.83	31	31	0.34	0.83	34			31			11	
ZACTIQUE® II	0818-0004	0.35	0.75	32	32	0.37	0.84	39		✓	32		✓	22	
ZINC GRAY	0818-0010	0.35	0.83	35	35	0.37	0.85	39		✓	35		✓	20	

<sup>A</sup> - All performance data for Zincalume Plus is based on actual testing (not color families)

ZINCALUME® is a registered trademark of BlueScope LTD